Concrete Test Report

Date : 06/24/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 05/22/2026 08:
Onsite Hours : 01:45

ASEC Report ID : 95459
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : Sunny
Departure Time : 05/22/2026 09:50
ASEC Technician Name : Charles Bolling

Location(S): Parkway Curb, 400 Courtesy Parkway SE.

Testing: 1 Set of concrete specimens (4 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☐Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 4 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks:

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.

Concrete Test Report

Date : 06/24/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 05/22/2026 08:
Onsite Hours : 01:45

ASEC Report ID : 95459
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : Sunny
Departure Time : 05/22/2026 09:50
ASEC Technician Name : Charles Bolling

PLACEMENT INFORMATION – Cylinder

Set Number: A
Date Sampled: 05/22/2026
Sampled By: Charles Bolling
Contractor: LAGNIAPPE Development Company
Truck Number: 2170
Time Batched: 08:33
Location of Placement: Parkway Curb, 400 Courtesy Parkway SE.
Number of Samples Cast: 4
Ambient Temp (°f): 74
Slump (in.): 6.25

Laboratory Number: 2026-168
Time Sampled: 08:51
Concrete Supplier: Thomas
Mix ID: 228000 GDOT Class B Fly
Quantity of Load: 9
Specified Strength: 2200
Concrete Temp (°f): 71
Air Content (%): 4.5
Unit Weight (pcf): 142.4
Water Added (gal.): N/A

Specimen Number	Scheduled Test Date	Date Tested	Age (Days)	Dia (in.)	Area (sq in.)	Max Load (lbf)	Strength (psi)	% Design Strength	Fracture Type
1	05/29/2026	05/29/2026	7	5.99	28.13	57411	2040	92.7	Type 5
2	06/19/2026	06/19/2026	28	5.99	28.13	104555	3720	169.1	Type 5
3	06/19/2026	06/19/2026	28	5.99	28.13	105106	3740	170.0	Type 5

UNLESS OTHERWISE SPECIFIED, TESTS WERE PERFORMED IN ACCORDANCE WITH ASTM METHODS C31, C39, C138, C143, C173, C1064.

(1) Cone (2) Cone-split (3) Vertical (4) Shear (5) Edge Fracture (6) Pointed

Catherine Lanier
Lab Manager

Kenneth Mosman