Concrete Test Report

Date : 06/10/2026
Project No : 2026C138
Client Company : CWM
Arrival Time : 06/10/2026 22:00
Onsite Hours : 06:00

ASEC Report ID : 95274
Name of the Project : Bouldercrest Road Ramps off of I-20
Project Location : Atlanta
Weather : clear
Departure Time : 06/11/2026 04:00
ASEC Technician Name : Samara Simha Reddy Kandi

Location(S):

Testing: 1 Set of concrete specimens (2 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☐Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 2 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks:

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.

AS Engineering and Consulting LLC

Concrete Test Report

Date : 06/10/2026
Project No : 2026C138
Client Company : CWM
Arrival Time : 06/10/2026 22:00
Onsite Hours : 06:00

ASEC Report ID : 95274
Name of the Project : Bouldercrest Road Ramps off of I-20
Project Location : Atlanta
Weather : clear
Departure Time : 06/11/2026 04:00
ASEC Technician Name : Samara Simha Reddy Kandi

PLACEMENT INFORMATION – Cylinder

Set Number: A
Date Sampled: 06/10/2026
Sampled By: Samara Simha Reddy Kandi
Contractor: CWM
Truck Number: 3
Time Batched: 23:15
Location of Placement: N/A
Number of Samples Cast: 2
Ambient Temp (°f): 77
Slump (in.): 1.5

Laboratory Number: N/A
Time Sampled: 23:50
Concrete Supplier: N/A
Mix ID: N/A
Quantity of Load: 10
Specified Strength: 3000
Concrete Temp (°f): 80
Air Content (%): 6
Unit Weight (pcf): 140
Water Added (gal.): N/A

Specimen Number	Scheduled Test Date	Date Tested	Age (Days)	Dia (in.)	Area (sq in.)	Max Load (lbf)	Strength (psi)	% Design Strength	Fracture Type
1	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A
2	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A	N/A

UNLESS OTHERWISE SPECIFIED, TESTS WERE PERFORMED IN ACCORDANCE WITH ASTM METHODS C31, C39, C138, C143, C173, C1064.

(1) Cone (2) Cone-split (3) Vertical (4) Shear (5) Edge Fracture (6) Pointed

Kenneth Mosman

Kenneth Mosman