Concrete Test Report

Date : 04/13/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 04/14/2026 11:30
Onsite Hours : 02:00

ASEC Report ID : 94172
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : Partly Cloudy
Departure Time : 04/14/2026 13:30
ASEC Technician Name : Zabihullah Lodin

Location(S): Levelling pad for MSE Wall #2

Testing: 1 Set of concrete specimens (5 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☐Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 5 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks:

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.

AS Engineering and Consulting LLC

Concrete Test Report

Date : 04/13/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 04/14/2026 11:30
Onsite Hours : 02:00

ASEC Report ID : 94172
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : Partly Cloudy
Departure Time : 04/14/2026 13:30
ASEC Technician Name : Zabihullah Lodin

PLACEMENT INFORMATION – Cylinder

Set Number: A
Date Sampled: 04/14/2026
Sampled By: Zabihullah Lodin
Contractor: WSP
Truck Number: 111
Time Batched: 11:06
Location of Placement: Levelling pad for MSE Wall #2
Number of Samples Cast: 5
Ambient Temp (°f): 75
Slump (in.): 3

Laboratory Number: 2026-102
Time Sampled: 12:37
Concrete Supplier: Ernst
Mix ID: Class A C-Ash
Quantity of Load: 8
Specified Strength: 4000
Concrete Temp (°f): 79
Air Content (%): 5
Unit Weight (pcf): N/A
Water Added (gal.): N/A

Specimen Number	Scheduled Test Date	Date Tested	Age (Days)	Dia (in.)	Area (sq in.)	Max Load (lbf)	Strength (psi)	% Design Strength	Fracture Type
1	04/21/2026	04/21/2026	7	3.98	12.41	65598	5290	N/A	Type 2
2	05/11/2026	05/11/2026	27	3.98	12.41	73627	5930	N/A	Type 1
3	05/12/2026	05/12/2026	28	3.98	12.41	76103	6130	N/A	Type 5
4	05/12/2026	05/12/2026	28	3.98	12.41	77254	6230	N/A	Type 5
5	06/08/2026	06/08/2026	55	3.98	12.41	83988	6770	N/A	Type 2

UNLESS OTHERWISE SPECIFIED, TESTS WERE PERFORMED IN ACCORDANCE WITH ASTM METHODS C31, C39, C138, C143, C173, C1064.

(1) Cone (2) Cone-split (3) Vertical (4) Shear (5) Edge Fracture (6) Pointed

Catherine Lanier
Lab Manager

Kenneth Mosman