Concrete Test Report

Date : 07/07/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 07/07/2026 9:00
Onsite Hours : 03:00

ASEC Report ID : 95990
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : clear and sunny
Departure Time : 07/07/2026 12::0
ASEC Technician Name : Narayana Ganesh Undavalli

Location(S):

Testing: 1 Set of concrete specimens (2 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☐Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 2 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks: Test 1 Temp of concrete = 88 Amb temp = 81 Slump = 4 air = 4 unit wt of concrete = 145.

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.