Concrete Test Report

Date : 07/23/2026
Project No : 2026C115-WO 1
Client Company : WSP
Arrival Time : 07/23/2026 03:00
Onsite Hours : 04:00

ASEC Report ID : 96330
Name of the Project : Lanier Islands Parkway
Project Location : Buford
Weather : Clear
Departure Time : 07/23/2026 07:00
ASEC Technician Name : Charles Bolling

Location(S):

Testing: 1 Set of concrete specimens (5 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☒Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 5 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks:

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.

Concrete Test Report

Date : 07/23/2026
Project No : 2026C115-WO 1
Client Company : WSP
Arrival Time : 07/23/2026 03:00
Onsite Hours : 04:00

ASEC Report ID : 96330
Name of the Project : Lanier Islands Parkway
Project Location : Buford
Weather : Clear
Departure Time : 07/23/2026 07:00
ASEC Technician Name : Charles Bolling

PLACEMENT INFORMATION – Cylinder

Set Number:	N/A	**Laboratory Number:**	N/A
Date Sampled:	N/A	**Time Sampled:**	04:08
Sampled By:	Charles Bolling	**Concrete Supplier:**	Morgan concrete company inc
Contractor:	conbuf	**Mix ID:**	405789CSOG
Truck Number:	418	**Quantity of Load:**	10
Time Batched:	03:47	**Specified Strength:**	4000
Location of Placement:	N/A	**Concrete Temp (°f):**	85
Number of Samples Cast:	5	**Air Content (%):**	2
Ambient Temp (°f):	75	**Unit Weight (pcf):**	131
Slump (in.):	6	**Water Added (gal.):**	N/A

Specimen Number	Scheduled Test Date	Date Tested	Age (Days)	Dia (in.)	Area (sq in.)	Max Load (lbf)	Strength (psi)	% Design Strength	Fracture Type
No test results available									

UNLESS OTHERWISE SPECIFIED, TESTS WERE PERFORMED IN ACCORDANCE WITH ASTM METHODS C31, C39, C138, C143, C173, C1064.

(1) Cone (2) Cone-split (3) Vertical (4) Shear (5) Edge Fracture (6) Pointed

Kenneth Mosman

Kenneth Mosman