Concrete Test Report

Date : 05/11/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 05/11/2026 11:00
Onsite Hours : 01:30

ASEC Report ID : 95099
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : N/A
Departure Time : 05/11/2026 12:30
ASEC Technician Name : Michael Cius

Location(S): L Line Headwall

Testing: 1 Set of concrete specimens (3 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☐Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 3 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks:

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.

Concrete Test Report

Date : 05/11/2026
Project No : 2026C122
Client Company : WSP
Arrival Time : 05/11/2026 11:00
Onsite Hours : 01:30

ASEC Report ID : 95099
Name of the Project : Courtesy Pkwy Expansion
Project Location : Conyers
Weather : N/A
Departure Time : 05/11/2026 12:30
ASEC Technician Name : Michael Cius

PLACEMENT INFORMATION – Cylinder

Set Number: 1
Date Sampled: 05/11/2026
Sampled By: Michael Cius
Contractor: AL Lewis Construction Inc.
Truck Number: 2137
Time Batched: 11:21
Location of Placement: L Line Headwall
Number of Samples Cast: 3
Ambient Temp (°f): N/A
Slump (in.): 4.5

Laboratory Number: 2026-142
Time Sampled: 11:30
Concrete Supplier: N/A
Mix ID: 228000
Quantity of Load: 8
Specified Strength: GDOT Class B Specification
Concrete Temp (°f): 80
Air Content (%): 4
Unit Weight (pcf): N/A
Water Added (gal.): N/A

Specimen Number	Scheduled Test Date	Date Tested	Age (Days)	Dia (in.)	Area (sq in.)	Max Load (lbf)	Strength (psi)	% Design Strength	Fracture Type
1	06/08/2026	06/08/2026	28	3.98	12.44	46906	3770	N/A	Type 5
2	06/08/2026	06/08/2026	28	3.98	12.44	44043	3540	N/A	Type 6
3	06/08/2026	06/08/2026	28	3.98	12.44	47213	3800	N/A	Type 5

UNLESS OTHERWISE SPECIFIED, TESTS WERE PERFORMED IN ACCORDANCE WITH ASTM METHODS C31, C39, C138, C143, C173, C1064.

(1) Cone (2) Cone-split (3) Vertical (4) Shear (5) Edge Fracture (6) Pointed

Catherine Lanier
Lab Manager

Kenneth Mosman