Concrete Test Report

Date : 08/13/2026
Project No : 2023C159
Client Company : CW Matthews
Arrival Time : 08/13/2026 8:00
Onsite Hours : 08:00

ASEC Report ID : 96969
Name of the Project : Airfield Repairs 2021-23
Project Location : HJAIA, Atlanta, GA
Weather : clear and sunny
Departure Time : 08/13/2026 16:00
ASEC Technician Name : Narayana Ganesh Undavalli

Location(S): CONCRETE STRUCTURE

Testing: 1 Set of concrete specimens (4 per set) were cast during the cast-in-place concrete pour at the above referenced location, in accordance with ASTM C31. The specimen will remain on site for the initial 24-48 hrs curing.

Compliance: ☒Field placement of concrete appeared to be in general accordance with the project specifications (i.e., slump, temperature, etc) (refer to remarks below)
☐Deviations and/or noncompliances were noted during the field placement (refer to remarks below)

Specimen Pick Up: 1 Sets of concrete specimens/ 4 specimen per set were picked up & transported to AS Engineering and Consulting LLC (ASEC) for curing and testing in accordance with ASTM C39, C670/1231

Field Curing: Specimen were stored for the initial 24 hours
☒ Near the poured structure
☐ In an insulated curing box
☐ Other

Remarks:

The results presented in this report relate only to the items tested. This report shall not be reproduced, except in full, without written approval from AS Engineering and Consultiing LLC.

AS Engineering and Consulting LLC

Concrete Test Report

Date : 08/13/2026
Project No : 2023C159
Client Company : CW Matthews
Arrival Time : 08/13/2026 8:00
Onsite Hours : 08:00

ASEC Report ID : 96969
Name of the Project : Airfield Repairs 2021-23
Project Location : HJAIA, Atlanta, GA
Weather : clear and sunny
Departure Time : 08/13/2026 16:00
ASEC Technician Name : Narayana Ganesh Undavalli

PLACEMENT INFORMATION – Cylinder

Set Number:	A	**Laboratory Number:**	N/A
Date Sampled:	08/13/2026	**Time Sampled:**	11:30
Sampled By:	Narayana Ganesh Undavalli	**Concrete Supplier:**	Thomas concrete
Contractor:	curb and gutter contracting co.	**Mix ID:**	GDOT CLASS A FLY
Truck Number:	1932	**Quantity of Load:**	8
Time Batched:	10:37	**Specified Strength:**	N/A
Location of Placement:	CONCRETE STRUCTURE	**Concrete Temp (°f):**	85
Number of Samples Cast:	4	**Air Content (%):**	5
Ambient Temp (°f):	88	**Unit Weight (pcf):**	148
Slump (in.):	4	**Water Added (gal.):**	5

Specimen Number	Scheduled Test Date	Date Tested	Age (Days)	Dia (in.)	Area (sq in.)	Max Load (lbf)	Strength (psi)	% Design Strength	Fracture Type
No test results available									

UNLESS OTHERWISE SPECIFIED, TESTS WERE PERFORMED IN ACCORDANCE WITH ASTM METHODS C31, C39, C138, C143, C173, C1064.

(1) Cone (2) Cone-split (3) Vertical (4) Shear (5) Edge Fracture (6) Pointed

Kenneth Mosman

Kenneth Mosman